

ISSN 2518-1491 (Online),  
ISSN 2224-5286 (Print)

ҚАЗАҚСТАН РЕСПУБЛИКАСЫ  
ҰЛТТЫҚ ҒЫЛЫМ АКАДЕМИЯСЫНЫҢ

Д.В.СОКОЛЬСКИЙ АТЫНДАҒЫ «ЖАНАРМАЙ»,  
КАТАЛИЗ ЖӘНЕ ЭЛЕКТРОХИМИЯ ИНСТИТУТЫ» АҚ

# Х А Б А Р Л А Р Ы

## ИЗВЕСТИЯ

НАЦИОНАЛЬНОЙ АКАДЕМИИ НАУК  
РЕСПУБЛИКИ КАЗАХСТАН

АО «ИНСТИТУТ ТОПЛИВА, КАТАЛИЗА И  
ЭЛЕКТРОХИМИИ ИМ. Д.В. СОКОЛЬСКОГО»

## NEWS

OF THE ACADEMY OF SCIENCES  
OF THE REPUBLIC OF KAZAKHSTAN

JSC «D.V. SOKOLSKY INSTITUTE OF FUEL,  
CATALYSIS AND ELECTROCHEMISTRY»

## ХИМИЯ ЖӘНЕ ТЕХНОЛОГИЯ СЕРИЯСЫ

### ◆ СЕРИЯ ХИМИИ И ТЕХНОЛОГИИ

### ◆ SERIES CHEMISTRY AND TECHNOLOGY

**5 (431)**

ҚЫРКҮЙЕК – ҚАЗАН 2018 ж.  
СЕНТЯБРЬ – ОКТЯБРЬ 2018 г.  
SEPTEMBER – OCTOBER 2018

1947 ЖЫЛДЫН ҚАҢТАР АЙЫНАН ШЫҒА БАСТАҒАН  
ИЗДАЕТСЯ С ЯНВАРЯ 1947 ГОДА  
PUBLISHED SINCE JANUARY 1947

ЖЫЛЫНА 6 РЕТ ШЫҒАДЫ  
ВЫХОДИТ 6 РАЗ В ГОД  
PUBLISHED 6 TIMES A YEAR

---

---

*NAS RK is pleased to announce that News of NAS RK. Series of chemistry and technologies scientific journal has been accepted for indexing in the Emerging Sources Citation Index, a new edition of Web of Science. Content in this index is under consideration by Clarivate Analytics to be accepted in the Science Citation Index Expanded, the Social Sciences Citation Index, and the Arts & Humanities Citation Index. The quality and depth of content Web of Science offers to researchers, authors, publishers, and institutions sets it apart from other research databases. The inclusion of News of NAS RK. Series of chemistry and technologies in the Emerging Sources Citation Index demonstrates our dedication to providing the most relevant and influential content of chemical sciences to our community.*

Қазақстан Республикасы Ұлттық ғылым академиясы "ҚР ҰҒА Хабарлары. Химия және технология сериясы" ғылыми журналының Web of Science-тің жаңаланған нұсқасы Emerging Sources Citation Index-те индекстелуге қабылданғанын хабарлайды. Бұл индекстелу барысында Clarivate Analytics компаниясы журналды одан әрі the Science Citation Index Expanded, the Social Sciences Citation Index және the Arts & Humanities Citation Index-ке қабылдау мәселесін қарастыруды. Web of Science зерттеушілер, авторлар, баспашилар мен мекемелерге контент тереңдігі мен сапасын ұсынады. ҚР ҰҒА Хабарлары. Химия және технология сериясы Emerging Sources Citation Index-ке енүі біздің қоғамдастық үшін ең өзекті және беделді химиялық ғылымдар бойынша контентке адалдығымызды білдіреді.

НАН РК сообщает, что научный журнал «Известия НАН РК. Серия химии и технологий» был принят для индексирования в Emerging Sources Citation Index, обновленной версии Web of Science. Содержание в этом индексировании находится в стадии рассмотрения компанией Clarivate Analytics для дальнейшего принятия журнала в the Science Citation Index Expanded, the Social Sciences Citation Index и the Arts & Humanities Citation Index. Web of Science предлагает качество и глубину контента для исследователей, авторов, издателей и учреждений. Включение Известия НАН РК в Emerging Sources Citation Index демонстрирует нашу приверженность к наиболее актуальному и влиятельному контенту по химическим наукам для нашего сообщества.

**Бас редакторы**  
х.ғ.д., проф., ҚР ҮҒА академигі **М.Ж. Жұрынов**

Редакция алқасы:

**Агабеков В.Е.** проф., академик (Белорус)  
**Волков С.В.** проф., академик (Украина)  
**Воротынцев М.А.** проф., академик (Ресей)  
**Газалиев А.М.** проф., академик (Қазақстан)  
**Ергожин Е.Е.** проф., академик (Қазақстан)  
**Жармағамбетова А.К.** проф. (Қазакстан), бас ред. орынбасары  
**Жоробекова Ш.Ж.** проф., академик (Қырғыстан)  
**Иткулова Ш.С.** проф. (Қазақстан)  
**Манташян А.А.** проф., академик (Армения)  
**Пралиев К.Д.** проф., академик (Қазақстан)  
**Баешов А.Б.** проф., академик (Қазакстан)  
**Бұркітбаев М.М.** проф., академик (Қазақстан)  
**Джусипбеков У.Ж.** проф. корр.-мүшесі (Қазақстан)  
**Молдахметов М.З.** проф., академик (Қазақстан)  
**Мансуров З.А.** проф. (Қазақстан)  
**Наурызбаев М.К.** проф. (Қазақстан)  
**Рудик В.** проф., академик (Молдова)  
**Рахимов К.Д.** проф. академик (Қазақстан)  
**Стрельцов Е.** проф. (Белорус)  
**Тәшімов Л.Т.** проф., академик (Қазақстан)  
**Тодераш И.** проф., академик (Молдова)  
**Халиков Д.Х.** проф., академик (Тәжікстан)  
**Фарзалиев В.** проф., академик (Әзірбайжан)

**«ҚР ҮҒА Хабарлары. Химия және технология сериясы».**

**ISSN 2518-1491 (Online),**

**ISSN 2224-5286 (Print)**

Меншіктенуші: «Қазақстан Республикасының Ұлттық ғылым академиясы» Республикалық қоғамдық бірлестігі (Алматы қ.)

Қазақстан республикасының Мәдениет пен ақпарат министрлігінің Ақпарат және мұрағат комитетінде 30.04.2010 ж. берілген №1089-Ж мерзімдік басылым тіркеуіне қойылу туралы күзелік

Мерзімділігі: жылына 6 рет.

Тиражы: 300 дана.

Редакцияның мекенжайы: 050010, Алматы қ., Шевченко көш., 28, 219 бөл., 220, тел.: 272-13-19, 272-13-18,  
[www.nauka-nanrk.kz](http://www.nauka-nanrk.kz) / [chemistry-technology.kz](http://chemistry-technology.kz)

---

© Қазақстан Республикасының Ұлттық ғылым академиясы, 2018

Типографияның мекенжайы: «Аруна» ЖК, Алматы қ., Муратбаева көш., 75.

Г л а в н ы й р е д а к т о р  
д.х.н., проф.,академик НАН РК **М. Ж. Журинов**

Р е д а к ц и о н на я к ол л е г и я:

**Агабеков В.Е.** проф., академик (Беларусь)  
**Волков С.В.** проф., академик (Украина)  
**Воротынцев М.А.** проф., академик (Россия)  
**Газалиев А.М.** проф., академик (Казахстан)  
**Ергожин Е.Е.** проф., академик (Казахстан)  
**Жармагамбетова А.К.** проф. (Казахстан), зам. гл. ред.  
**Жоробекова Ш.Ж.** проф., академик (Кыргызстан)  
**Иткулова Ш.С.** проф. (Казахстан)  
**Манташян А.А.** проф., академик (Армения)  
**Пралиев К.Д.** проф., академик (Казахстан)  
**Баешов А.Б.** проф., академик (Казахстан)  
**Буркитбаев М.М.** проф., академик (Казахстан)  
**Джусипбеков У.Ж.** проф. чл.-корр. (Казахстан)  
**Мулдахметов М.З.** проф., академик (Казахстан)  
**Мансуров З.А.** проф. (Казахстан)  
**Наурызбаев М.К.** проф. (Казахстан)  
**Рудик В.** проф.,академик (Молдова)  
**Рахимов К.Д.** проф. академик (Казахстан)  
**Стрельцов Е.** проф. (Беларусь)  
**Ташимов Л.Т.** проф., академик (Казахстан)  
**Тодераш И.** проф., академик (Молдова)  
**Халиков Д.Х.** проф., академик (Таджикистан)  
**Фарзалиев В.** проф., академик (Азербайджан)

**«Известия НАН РК. Серия химии и технологии».**

**ISSN 2518-1491 (Online),**

**ISSN 2224-5286 (Print)**

Собственник: Республиканское общественное объединение «Национальная академия наук Республики Казахстан» (г. Алматы)

Свидетельство о постановке на учет периодического печатного издания в Комитете информации и архивов Министерства культуры и информации Республики Казахстан №10893-Ж, выданное 30.04.2010 г.

Периодичность: 6 раз в год

Тираж: 300 экземпляров

Адрес редакции: 050010, г. Алматы, ул. Шевченко, 28, ком. 219, 220, тел. 272-13-19, 272-13-18,  
<http://nauka-nanrk.kz> / [chemistry-technology.kz](http://chemistry-technology.kz)

---

© Национальная академия наук Республики Казахстан, 2018

Адрес редакции: 050100, г. Алматы, ул. Кунаева, 142,  
Институт органического катализа и электрохимии им. Д. В. Сокольского,  
каб. 310, тел. 291-62-80, факс 291-57-22, e-mail:[orgcat@nursat.kz](mailto:orgcat@nursat.kz)

Адрес типографии: ИП «Аруна», г. Алматы, ул. Муратбаева, 75

Editor in chief  
doctor of chemistry, professor, academician of NAS RK **M.Zh. Zhurinov**

Editorial board:

**Agabekov V.Ye.** prof., academician (Belarus)  
**Volkov S.V.** prof., academician (Ukraine)  
**Vorotyntsev M.A.** prof., academician (Russia)  
**Gazaliyev A.M.** prof., academician (Kazakhstan)  
**Yergozhin Ye.Ye.** prof., academician (Kazakhstan)  
**Zharmagambetova A.K.** prof. (Kazakhstan), deputy editor in chief  
**Zhorobekova Sh.Zh.** prof., academician (Kyrgyzstan)  
**Itkulova Sh.S.** prof. (Kazakhstan)  
**Mantashyan A.A.** prof., academician (Armenia)  
**Praliyev K.D.** prof., academician (Kazakhstan)  
**Bayeshov A.B.** prof., academician (Kazakhstan)  
**Burkitbayev M.M.** prof., academician (Kazakhstan)  
**Dzhusipbekov U.Zh.** prof., corr. member (Kazakhstan)  
**Muldakhmetov M.Z.** prof., academician (Kazakhstan)  
**Mansurov Z.A.** prof. (Kazakhstan)  
**Nauryzbayev M.K.** prof. (Kazakhstan)  
**Rudik V.** prof., academician (Moldova)  
**Rakhimov K.D.** prof., academician (Kazakhstan)  
**Streltsov Ye.** prof. (Belarus)  
**Tashimov L.T.** prof., academician (Kazakhstan)  
**Toderash I.** prof., academician (Moldova)  
**Khalikov D.Kh.** prof., academician (Tadzhikistan)  
**Farzaliyev V.** prof., academician (Azerbaijan)

**News of the National Academy of Sciences of the Republic of Kazakhstan. Series of chemistry and technology.**

**ISSN 2518-1491 (Online),**

**ISSN 2224-5286 (Print)**

Owner: RPA "National Academy of Sciences of the Republic of Kazakhstan" (Almaty)

The certificate of registration of a periodic printed publication in the Committee of Information and Archives of the Ministry of Culture and Information of the Republic of Kazakhstan N 10893-Ж, issued 30.04.2010

Periodicity: 6 times a year

Circulation: 300 copies

Editorial address: 28, Shevchenko str., of. 219, 220, Almaty, 050010, tel. 272-13-19, 272-13-18,  
<http://nauka-nanrk.kz> / [chemistry-technology.kz](http://chemistry-technology.kz)

---

© National Academy of Sciences of the Republic of Kazakhstan, 2018

Editorial address: Institute of Organic Catalysis and Electrochemistry named after D. V. Sokolsky  
142, Kunayev str., of. 310, Almaty, 050100, tel. 291-62-80, fax 291-57-22,  
e-mail: orgcat@nursat.kz

Address of printing house: ST "Aruna", 75, Muratbayev str, Almaty

**NEWS**

OF THE NATIONAL ACADEMY OF SCIENCES OF THE REPUBLIC OF KAZAKHSTAN

**SERIES CHEMISTRY AND TECHNOLOGY**

ISSN 2224-5286

<https://doi.org/10.32014/2018.2518-1491.5>

Volume 5, Number 431 (2018), 32 – 40

**Ye.V. Apimakh<sup>1</sup>, A.E. Leudanski<sup>1</sup>, V.G. Golubev<sup>2</sup>,  
B.N. Korganbayev<sup>2</sup>, D. Sarsenbekuly<sup>2</sup>**

<sup>1</sup>Belarusian State Technological University, Minsk city, Belarus;

<sup>2</sup>M.Auezov South Kazakhstan State University, Shymkent city, Kazakhstan

e.mail: nii\_mm@mail.ru

## **PROMISING DIRECTIONS OF REDUCING SPECIFIC ENERGY COSTS IN GRINDING**

**Abstract.** The grinding process is widely used in various technologies and is characterized by high energy consumption. Besides, there is an irretrievable loss of high-quality steel due to the wear of the working elements of grinders.

High energy costs occur not only due to the large volumes of processed materials, but also due to the extremely low efficiency of grinding machines, especially mills, the efficiency coefficient of which is at best several percents. Especially sharply the efficiency coefficient is reducing and the mills' drive capacity is increasing with an increase in the milling fineness of the material.

Despite the new methods of grinding: electro-hydraulic, ultrasonic, gravitational, light beam grinding, etc., in all designs of industrial units the grinding, is carried out by mechanical methods, such as crushing, cracking, impact, attrition, breakage or a combination of these methods.

There is carried out the analysis of energy costs for formation of new surfaces, elastic and plastic deformations, for formation of various kinds of defects in the crystal structure (mainly dislocations), for friction of the material's particles between themselves and the walls of the grinding chamber. It is noted that a small part of the input energy is consumed by different kinds of radiation (acoustic waves, exoelectronic emission, etc.), which always accompany the destruction.

From the analysis carried out it follows that the lowest energy intensity of the grinding process is achieved in grinding due to impact and slightly worse - due to crushing. When grinding by impact, the loading of the material should be pulsed with the steepest front. The loads must be dosed, corresponding to the strength and endurance of the defective zones.

To the working zone of the mill the starting material should be supplied in small volumes and even better piece by piece, and after grinding - quickly removed from the milling zone to the classifier. Therefore, any mill should operate in a closed cycle.

The classifier must be of high efficiency, so that to the finished product there came the particles of only smaller than the near-mesh grain, and the large fraction, returned to re-milling, contained as few particles of the finished product as possible.

**Keywords:** grinders, mills, energy costs, milling fineness, crushing, cracking, attrition, breakage, impact, classifier, closed cycle.

**Introduction.** Intensification of technological processes with reducing the energy costs for their implementation is an urgent task of modern production. One of the main ways to solve this problem is the creation and implementation of new high-performance machines and devices with low energy consumption.

The problem of reducing energy costs and increasing the efficiency is particularly acute in carrying out the grinding process. This process is widely used in various technologies and is characterized by high energy consumption, while the equipment for its implementation is cumbersome and has low efficiency.

Large energy consumption in the process of grinding is confirmed by the fact that about 5–10% of the world's electricity is spent on this process [1, p.8; 2, p. 6], and even more, according to the statistical data on the United States mining industry [3, 4]. Besides, the irretrievable losses of high-quality steel due

to wear of the working elements of grinders are about 4 million tons per year. The mills' drive capacity in fine grinding of cement production, mining and other industries reaches up to 25MW [5, 6]. The size of mills at present has reached the limit of an economically viable size.

High energy costs occur not only due to the large volumes of processed materials, but also due to the extremely low efficiency of grinding machines, especially mills, the efficiency coefficient of which is at best several percents. Especially sharply the efficiency coefficient is reducing and the mills' drive capacity is increasing with an increase in the milling fineness of the material.

At the same time, by the studies of recent years, there has been revealed quite a number of mechanochemical phenomena, which are observed in fine and ultrafine grinding [7, p. 21-24]. For example, with the increase in the cement milling fineness, there increases the rate of its setting and there sharply increases the strength of the agglomerate. Rocks, such as granite, schoenite and others, acquire cementing properties in this grinding. With the increase in the milling fineness of some substances, there increases not only the rate, but also the degree of their dissolution. Some pigments, depending on the milling fineness, change their color. With fine grinding of ores, the process of extracting minerals is very fast, with high completeness of their extraction. In a number of works [7, p. 22] there is noted the possibility of direct metal recovery by a mechanochemical method. This is not at all a complete list of phenomena, on the basis of which it is possible to create new high-performance technologies. However, economically it is possible only on the condition of considerable reduction of costs for grinding of the materials.

**The research methodology** is to carry out the analysis of the main energy consumption items in grinding and to develop the recommendations on rational organization of the grinding technology with optimal process conditions.

**Research results.** In all designs of industrial units the grinding is carried out by mechanical methods, such as crushing, cracking, impact, attrition, breakage or a combination of these methods.

In addition to mechanical methods, recently there have been proposed new methods of grinding: electrohydraulic, ultrasonic, gravitational, grinding with a light beam, obtained by means of a quantum generator, cavitation, grinding by rapidly changing high and low temperatures, grinding by a compressed gaseous medium energy, radiative and electromagnetic softening and others. However, the new methods have not yet come beyond the laboratory studies, and in the nearest future, the main units will remain mills, in which the grinding of the material is carried out by mechanical methods [2, p. 8]. Hence, to reduce the energy consumption and to improve the efficiency of the grinding process, it is necessary to further improve the existing grinding units and create fundamentally new designs.

Let's consider the main possible energy consumption items in grinding.

When grinding, the energy is spent not only on the formation of new surfaces, but also on the elastic and plastic deformations, on the formation of various kinds of defects in the crystal structure (mainly dislocations), on the friction of material particles between themselves and the walls of the grinding chamber. A small part of the input energy is consumed by different kinds of radiation (acoustic waves, exoelectronic emission, etc.), which always accompany the destruction [2, p. 153]. The value of each of the energy loss factors is not a constant value and varies quite sharply, depending on the nature of the material being destructed, the scale factor and the organization of the grinding process in each specific unit. Let us consider in more detail each of the above items.

With the destruction of a piece of material, the new surfaces appear, with the layer of molecules of these surfaces acquiring the excess energy, the so-called "surface energy of the body." This energy must be transferred to the body from the outside. The amount of surface energy, depending on the formed surface, is determined by the following dependence [8]:

$$A = A_{yo} \Delta S \quad (1)$$

where  $A$  – the work, spent on the increment  $\Delta S$  of the surface;  $A_{yo}$  – the work, spent on the formation of a unit of a new surface.

Theoretical calculations and experimental studies, conducted by many researchers, lead to paradoxical conclusions that the real strength of most minerals is two or three orders of magnitude less than the theoretical strength, while the real energy intensity of the destruction of these minerals is three or more orders of magnitude more than the theoretical energy intensity of the formation of a new surface [2, p. 34].

The differences between the theoretical strength of solids and the real one were explained by the works of A. Griffiths and A. Ioffe [9, p. 45-53; 10, p. 145-163]. According to the theory of Griffiths, strength is determined not by regular properties of the solid, but by defects, "inhabiting" it, primarily cracks. Based on this theory, he was the first to formulate an energy strength criterion, according to which a crack in a stressed body with fixed boundaries begins to develop at the moment, when it becomes energetically "profitable" to the body, namely, when the reduction of the deformation energy of the whole body, which occurred as a result of the crack opening, exceeds the energy of the surface, formed during this opening.

Later on, the results of a series of original studies were published by other scientists, having explained the nature of plastic deformation as a result of kinetic processes, occurring at the atomic level, which are associated with a discrete model of matter structure. The defects, in this case, are in the atomic structure of the substance itself, for example, vacancies, dislocations, disclinations in crystals [11, p. 140-146; 12, p. 104-114].

The material destruction process is to be considered as a multi-stage one and as interrelated at different scale levels. For example, it is necessary to consider the collective effects of dislocation systems, disclinations, further cracks, etc. Thus, in [13, 8] in general, the whole process of destruction is proposed to be divided into the following stages: preparatory, embryonic cracks, microcracks, macrocracks, the growth of main cracks. In certain cases, some stages may be missing.

The essential influence on energy costs in grinding is also made by the method of loading pieces of material. Thus, during compression, the elastic deformations in the milled body occur due to its loading in quasi-static or dynamic modes. In this case, the entire volume of the body is subjected to loading. At the same time, it is known that compression is far from being a rational method of destruction, and finally, the destruction occurs in those points of the body, where the tensile stresses are created above the critical ones. The entire volume of the piece is subjected to loading, and the work of external forces by the time of destruction becomes close to the value, when it is possible to destroy the whole sample into separate tiny particles, but the destruction occurs only on separate planes with a weakened bond. Therefore, the rest of the energy of elastic deformation, accumulated in the body, will pass into heat, that is, will be irretrievably lost. To reduce the energy consumption for elastic deformations, it would be very promising to carry out the local limit loading of the initial piece in the place of destruction. In this case, in the body the stress gradient will be observed, due to which the energy selectivity of destruction will be increasing. Pilot studies of this method are being carried out in Russia under the leadership of Yu. D. Krasnikov for the purpose of organizing the destruction of rocks with lower energy costs [14].

Some researchers [15, pp. 68-71] prove that under high speed impact loading, the compression force occurs in a certain section so fast that the crack is formed before the equilibrium distribution of energy is set in the particle, which is necessary for making a rupture. The experimental studies on impact destruction of glass balls, given in [16, p. 1053-1060], proved that the average work of grinding by impact is approximately 42% of the grinding work by crushing. In paper [17] Ye. M. Gutiyar also proves that under dynamic loading of materials the stresses arising are twice higher than under static loading. Apparently, this can be explained by the fact that under high-speed dynamic loading the elastic deformation, uniform throughout the whole volume, is not yet achieved, but due to a larger stress gradient, the destruction begins in the weakened places (sections). It should be noted that this position is also theoretically proved in the classical course of resistance of materials [18 p. 516; 19].

When grinding materials by force loading, in addition to elastic deformations, the pieces will be subjected to plastic deformations. G. S. Khodakov [1, p. 124-126] showed in his studies that even such fragile rocks like quartzite and jaspilite undergo plastic deformation. Thermal losses in the maximum plastic deformation can be more than a half of the entire work of destruction for most materials.

At high loading rates of the body under grinding, the plastic deformation is localized in a relatively small number of atomic layers, located directly in the region of formation of future fracture surfaces. Thus, in order to reduce the costs for plastic deformation, it is also necessary to increase the speed of loading the material with the optimally applied load.

In addition to energy losses for elastic and plastic deformations, a certain part of the energy will be spent on the formation of new defects in the crystal structure. The main part in this process will be occupied by the formation of dislocations. It should be noted that dislocations have a great influence on

the strength of crystals. Under the influence of an external load, dislocations easily move, interact with each other and with other defects, unite and come to the surface of the crystal. The very displacement of the structure by at least one row of atoms weakens the crystal, in addition, the dislocations contribute to the formation of embryonic cracks, developing further into cracks of destruction [20, p. 312].

For over a hundred years many researchers have been trying to identify the patterns, permitting to quantify the energy intensity of the grinding process. The first attempt to identify the energy costs for grinding was made by P. Rittinger. According to his hypothesis, it follows that the work, spent on grinding, is proportional to the size of the newly formed surface in the material under grinding:

$$A_{noe} = k_{noe} \delta^2 \quad (2)$$

where  $k_{noe}$  – the coefficient of proportionality.

By the supporters of this hypothesis, there were conducted numerous studies that prove the validity of the assumption of proportionality of the grinding work to the newly formed surface. However, this hypothesis does not take into account many factors, affecting the consumption energy and, above all, the energy, spent on deformation of the body without destruction.

A bit later, F. Kick and V. Kirpichev [20; 21] independently from each other put forward the hypothesis that the energy, required to obtain the similar changes in the configuration of geometrically similar bodies of the same technological structure, is changing just like the weight or volume of these bodies. Therefore, the work for grinding one piece of size  $\delta$  will be equal to:

$$A_{o\delta} = k_{o\delta} \delta^3 \quad (3)$$

where  $k_{o\delta}$  – the coefficient of proportionality.

The experimental test has shown that the hypothesis of Kick-Kirpichev is more or less true in crushing and completely inadequate in milling. F. Bond [20], believing that the full work should include the work of deformation and formation of new surfaces, proposed to consider the work, spent on the piece grinding, to be proportional to the geometric average of the volume and surface of the piece:

$$A = A_{o\delta} + A_{noe} = k_B \delta^{2.5} \quad (4)$$

For ball and rod mills, for hammer crushers and other designs of grinders in the grinding of certain rocks and ores, on the basis of experimental studies, there were obtained the specific values of the proportionality coefficient  $k_B$  (the so-called W-index of work according to F. Bond). The industrial tests have shown good convergence of recommendations for calculation of energy costs in crushing and milling by Bond's method, which ensured its application in practical calculations.

P. A. Rebinder [20; 21] also combined the hypotheses of Rittinger and Kick-Kirpichev, considering that the destruction occurs after deformation of the piece, and the total work of crushing is equal to the sum of deformation work and new surfaces' formation work:

$$A = A_{o\delta} + A_{noe} = k_{o\delta} \delta^3 + k_{noe} \delta^2 \quad (5)$$

From the physical point of view, the formula of P. A. Rebinder is more correct, since it indicates the multifactorial nature of the destruction process. However, to be limited to only two factors that determine the energy intensity of the grinding process would be wrong, since in the implementation of grinding there are a lot of other processes, proceeding simultaneously, which can consume a significant part of energy. Let's consider the main ones of them. The significant power consumption in grinding is associated with plastic deformations. Thus, in the work of G. S. Khodakov [1, p. 87-89] it is shown that almost all materials are subjected to plastic deformations, no matter how fragile they are. Thus, the analysis of the surface layer of quartz particles after grinding shows that it has not a crystalline, but an amorphous structure, and the thickness of this layer depends on the time and medium, in which the grinding was performed. The calculations show that energy losses on plastic deformations are most significant at a large specific surface area of the material to be destroyed and during a long stay in the grinding zone, i.e. in fine

grinding. Even such a fragile material as quartzite is subjected to plastic deformation and the energy losses for its maximum plastic deformation is about half of the entire work of destruction, and for such plastic rocks as marble and limestone – more than 80%. Since with the existing methods of grinding the plastic deformation occurs throughout the whole volume of the destroyed body, the volume of the plastic deformation region of the material's piece is proportional to the volume of this piece:

$$A_{nl} = k_{nl} \delta^3 \quad (6)$$

In addition to energy dissipation for elastic and plastic deformation, as well as energy consumption for new surfaces' formation, a certain part of the energy will be accumulated by the body in the form of energy of various newly formed defects in the crystal structure. The decisive role in this process will be played by dislocations. The calculations, given in the literature [2, p. 34-35], show that the maximum energy density that the body can store due to dislocation distortions of the crystal structure is of the order

$$B_{\kappa,\text{max}} \approx 10^7 \text{ Дж/м}^3 \quad (7)$$

The formation of crystal structure defects will occur in the entire volume of the material, hence the energy of defects, accumulated by the material, is proportional to  $\delta^3$ , and these losses can be recorded as:

$$A_o = k_o \delta^3 \quad (8)$$

The most significant energy consumption (especially in ball mills) occurs due to external friction, which is caused by resistance, arising between the particles, contacting under the action of the compressive load, with their relative movement in the plane of contact. External friction is the result of mechanical engagement and molecular adhesion between the surfaces and further elastic and plastic displacement and scratching of the material out, with the subsequent destruction and restoration of molecular bridges between the friction surfaces. The bulk of energy costs for external friction is not "accumulated" by the material's particles and all the more does not go to the formation of new surfaces, but dissipates into heat. Therefore, the larger the layer of material in the industrial apparatus and the higher the relative speed of the friction surfaces, the higher the energy consumption for external friction. This is confirmed by the works of German scientists of G. Rumpf's school [22, p. 79-85], which showed that the main energy losses in ball mills occur due to interaction of the material's particles.

According to calculations, made by Revnivtsev, the costs for friction of one piece are proportional to the linear size  $\delta$  of the latter in the degree of 2.5. Then the costs for friction will be:

$$A_{mp} = k_{mp} \delta^{2.5} \quad (9)$$

To complete the physical picture of costs for grinding, it is necessary to take into account the costs, associated with various types of radiation. First of all, these include the acoustic waves. In the general balance of energy consumption for grinding they are small. Since radiation comes as a rule from the surface layers of the newly formed surface, these costs can be taken into account by the following expression:

$$A_{u3l} = k_{u3l} \delta^2 \quad (10)$$

Deeming, that we have considered all the main known energy costs for grinding, the total costs will be equal to the amount of costs for volume and plastic deformations, formation of defects, formation of a new surface, external friction and radiation:

$$\begin{aligned} A &= A_{o6} + A_{no6} + A_{nl} + A_o + A_{mp} + A_{u3l} = \\ &= k_{o6} \delta^3 + k_{no6} \delta^2 + k_{nl} \delta^3 + k_o \delta^3 + k_{mp} \delta^{2.5} + k_{u3l} \delta^2 \end{aligned} \quad (11)$$

Each of the terms of this equation reflects a certain type of energy costs for processes, taking place in the grinder, and only the fourth term of the formula takes into account the useful work, spent on the formation of new surfaces. The percentage of each of the members of series (11) is not a constant value and will vary for different cases, depending on the nature of the material to be destructed, its size, the grinder's design and geometrical parameters.

The analysis of published works shows that in fine grinding of materials in the industrial designs of mills the value of useful costs, determined by the second member of the formula, does not exceed 3 percent of the total energy costs.

Of course, for further development of the grinding technology, it is necessary to develop successfully such sciences as solid state physics, fracture mechanics, etc. As for making some new "laws" of crushing, here the followingshould be noted. The natural heterogeneity of the materials, subjected to grinding, the unevenness of the stress field in the volume of the loaded piece, its anisotropy, multi-scale defects plus a variety of external factors (shape, material location, nature of movement of the machine's working parts, location of the crushed materialpieces, etc.) – make the problem of making the law of crushing, reflecting all aspects of modern technologies in terms of physics of this process, firstly, super-complex due to agreat number of parameters, and secondly, useless, because even in the hypothetical case, to use the record of a full formula of such a law would be impossible due to itsvastnesses.

In such a situation, it is quite natural that instead of the physical law for practical application there are more acceptablesimple statistical dependencies, convenient and describing close enough the phenomena in a certain range of each of the parameters of a certain design of agrinder.

However, the main task, facing both the theory and the practice of grinding, is to reduce the energy consumption in the implementation of this process. For this purpose, it is necessary to create fundamentally new, incomparably more effective methods of grinding, taking into account both the features of the natural properties of a particular material and the specifics of its further processing. First of all, it is necessary to work on the creation of more advanced designs of mills, in which the irretrievable energy losses, indicated in equation (11) by the first, third, fifth and sixth members,could be reduced to a minimum. The ways to solve this problem can be found in a detailed analysis of energy consumption items for specific structures, currently operated in the industrial production of grinding units [23-32].

Our critical analysis of the grinding process shows that the process of fine grinding (milling) is very energy-intensive, although the share of energy, spent on the disintegration of particles itself is very small and is equal to several percents. This occurs primarily due to imperfection of organization of the grinding processitself and due to low efficiency of the equipment,applied for these purposes.

To reduce energy costs, a rational organization of the grinding process should be provided, with optimal process conditions without excessive overgrinding with minimal effort and a high degree of destruction in one working cycle.

The lowest energy intensity of the grinding process is achieved in grinding by impact and slightly worse - by crushing.

When grinding by impact, the loading of the material should be pulsed with the steepest front; the loads should be dosed, corresponding to the strength and endurance of the defective zones.

To the working zone of the mill the starting material should be supplied in small volumes and even better piece by piece, and after grinding - quickly removed from the milling zone to the classifier. Therefore, any mill should operate in a closed cycle.

The classifier must be of highefficiency, so that to the finished product there came the particles of only smaller than the near-mesh grain, and the large fraction, returned forre-milling, contained as few particles of the finished product as possible.

### **Conclusions.**

For the process of grinding solid materials there iscarried out the analysis of energy costs for formation of new surfaces, elastic and plastic deformations,formation of various kinds of defects in the crystal structure, for friction of the material's particles between themselves and the walls of the grinding chamber, as well as for various kinds of radiation (acoustic waves, exoelectronic emission, etc.), which always accompany the destruction.

It is noted that the lowest energy intensity of the grinding process is achieved in grinding by impact and slightly worse -by crushing.

The recommendations are developed for organization of the optimal implementation of the processes of grinding and classification of solid materials.

#### REFERENCES

- [1] Hodakov G. S. Fizikaizmel'chenija. M.: Nauka, **1972**. 256 s.
- [2] Revnivcev V.I. Selektivnoerazrusheniemineralov. – M.: Nedra, **1988**.
- [3] BCS/U.S. Department of Energy Industrial Technologies Program: Mining Industry Energy Bandwidth Study, 2007, available at <http://www1.eere.energy.gov>, accessed April 2013.
- [4] U.S. Energy Information Administration: Annual Energy Review 2011, DOE/EIA-0384(**2011**), 2012.
- [5] Xstrata Technology: Isamill Website, 2013, available at <http://www.isamill.com>, accessed April 2013.
- [6] K. Andres, F. Haude, J. S. Afr. Inst. Min. Metall. 110, 125–131 (**2010**).
- [7] Mehanicheskiejavlenijaprisverhtonkomizmel'chenii: Sb. st. / Sibirskoeotdelenie AN SSSR.; Pod obshh. red. V. V. Zajceva. – Novosibirsk, **1971**. 255 s.
- [8] Hodakov G.S. Osnovnyemetodydispersnogoanalizaporoshkov. M.: Strojzdat, **1968**. 199 s.
- [9] Parton V.Z., Morozov E.M. Mehanikauprugoplasticheskogorazrushenija. M. Nauka, **1985**. 504 s.
- [10] Slepjan L.I. Mehanikatreshhin. L.: Sudostroenie, **1990**. 295 s.
- [11] Glushko A.I., Neshheretov I.I. O kineticheskompodhode k razrushenijugornyhporod. // Izv. AN SSSR. **1986**. № 6. s. 140-146.
- [12] Tomson R. Fizikarazrushenija. // V sb.: Atomistikarazrushenija. M.: Mir, 1987. S. 104 – 144.
- [13] Vladimirov V.I. Kinetikatreshhin i vakansij v kristallah. Avtoref. dis. d-rafiz.-mat. nauk. L., FTI, 1973. 41 s.
- [14] Issledovanijamehanizmarazrushenijaporodnogomassiva s pomoshh'jumashinmetatel'nogotipa / Ju.D. Krasnikov [i dr.] // Gornyjzhurnal. **2005**. № 9. S. 14–16.
- [15] Gijo, R. Problemaizmel'chenijamaterialov i eerazvitie / R. Gijo. M.: Strojzdat, **1964**. 112 s.
- [16] Kraus, V. Tehnikaizmel'chenija / V. Kraus. M.: Mashinostroenie, **1966**. – 1090 s.
- [17] Gut'jar, E.M. K ob#emnojteoriidroblenija / E.M. Gut'jar // IzvestijaMoskovskoj s.-h. akademiiim. Timirjazeva. **1961**. № 4. – S. 163–166.
- [18] Beljaev N. M. Soprotivleniematerialov, Glavnajaredakcijafiziko-matematicheskoyliteraturyizd-va «Nauka», **1976** g., str. 608.
- [19] Feodos'ev V.I. Soprotivleniematerialov: Ucheb. dljavuzov. - 10-e izdanie, pererab. idop. M.: Izd-vo MGTU im. N.Je.Baumana, **1999**. 592 s.
- [20] Andreev, S.E. Droblenie, izmel'chenie i grohocheniepoleznyhiskopakaemyh / S.E. Andreev, V.A. Perov, V.V. Zverevich. M.: Nedra, 1980. 415 s.
- [21] Sidenko P. M. Izmel'chenie v himicheskoypromyshlennosti. M.: Himija, **1977**. 382 s.
- [22] Rumpf H. The physical mechanism of the formation metal microspores in the wear process. J. Phys. D: Appl. Phys. **1970**. Vol. 8. P. 79 – 85.
- [23] DeshkoJu. I., Krejmer M. B., Kryhtin G. S. Izmel'cheniematerialov v cementnojpromyshlennosti. – M.: Izd. liter. postroitel'stu, 1966. – 274 s.
- [24] Tendencijarazvitijamolotkovyhmel'nic s separatorami. Obzor.Jenergeticheskoyashinostroenie, 1976. 62 s.
- [25] Cherek I.L., Belkoskij G.V. Povyshenieproizvoditel'nosticementnyhmel'nic. Cement № 3, **1956**. S. 13-14.
- [26] Kryhtin G.S. Vlijanieventilaciinaosnovnyepokazatelirabotytrubnyhcementnyhmel'nic./ Trudy NIicementa, vyp 12, **1959**. 86 s.
- [27] Tovarov V.V. Putipovyshenijaproizvoditel'nostimel'nic.// Cement № 2, **1962**. S 16-17.
- [28] N. Hlabangana, G. Danha, E. Muzenda. Effect of ball and feed particle size distribution on the milling efficiency of a ball mill: An attainable region approach. South African Journal of Chemical Engineering, Vol. 25, **2018**, P. 79-84
- [29] L. Little, A. NjemaMainza, M. Becker, J. Wiese. Fine grinding: How mill type affects particle shape characteristics and mineral liberation. Minerals Engineering, Vol. 111, **2017**, P. 148-157
- [30] A. Boehm, P. Meissner, T. Plochberger. An energy based comparison of vertical roller mills and tumbling mills. International Journal of Mineral Processing, Vol. 136, **2015**, P. 37-41
- [31] Levdanskij Je. I., Levdanskij A. Je. Jenergosberezeniepriizmel'cheniematerialov: Ucheb. posobie / Belorus. gos. tehnolog. un-t. Minsk, **1999**. 88 s.
- [32] Levdanskij A. Je., LevdanskijJe.I. Vysokojeffektivnyeprotochnyeprocessy i apparaty. Mn.: BGTU, **2001**. 234 s.

**Е.В. Опимах<sup>1</sup>, А.Э. Левданский<sup>1</sup>, В.Г. Голубев<sup>2</sup>, Б.Н. Корганбаев, Д. Сарсенбекулы<sup>2</sup>**

<sup>1</sup> Белорусский государственный технологический университет, г. Минск, Беларусь;

<sup>2</sup> М.Әуезов атындағы Оңтүстік Қазақстан мемлекеттік университеті, Шымкент, Қазақстан

## **ҰСАҚТАУ БАРЫСЫНДАҒЫ МЕНШІКТІ ЭНЕРГИЯ ШЫҒЫНДАРЫН ТӨМЕНДЕТУДІҢ КЕЛЕШЕКТІ БАҒЫТТАРЫ**

**Аннотация.** Ұсақтау процесі әр түрлі технологияларда кеңінен қолданыс табады және жоғары энергия тұтынумен ерекшеленеді. Одан басқа, ұсақтағыштың жұмыс элементтерінің тозуына байланысты жоғары сапалы болаттың қайтарымсыз жоғалулары болады.

Жоғары энергетикалық шығындар тек өндөлетін материалдардың ауқымды қолемінен ғана емес, ұсақтаушы машиналардың аса төмен тиімділігімен түсіндіріледі, олардың пайдалы әсер коэффициенті (ПӘК) әрі кетсе бірнеше пайызды құрайды. Әсіреле материалдың ұнтақтық жұқағының үлкеюімен дірменнің жетегінің қуаты артып бірден ПӘК-і төмендейді.

Ұсақтаудың жаңа әдістеріне қарамастан: электригидравликалық, ультрадыбысты, гравитационды, жарық сәулесімен ұсақтау және т.б., өнеркәсіптік агрегаттардың барлық конструкцияларында ұсақтау мыжғылау, уату, соққы, ұнтақтау, сындыру сияқты механикалық тәсілдермен немесе осы тәсілдерді үйлестірумен жүзеге асырылады.

Жаңа беттердің пайда болуына кететін энергия шығындарына, серпімділік және пластикалық деформациясына, кристалды құрылымның әр түрлі ақау түрлерінің пайда болуына (негізінен дислокация), ұсақтағыш камера қабырғалары мен материал болшектерінің өзара үйкелісіне сараптама жүргізілді. Жеткізілетін энергияның шамалы болігі әрқашан қиратуларды сүйемелдейтін әр түрлі сәулеленулерге (акустикалық толқындарға, экзоэлектронды эмиссияға) жұмысалатыны атап көрсетілді.

Жүргізілген сараптамадан ұсақтау процесінің неғұрлым төмен энергия сыйымдылығы соққы есебінен ұсақтау кезінде және біршама нашар мыжғылау есебінен қол жеткізілетінін анғаруға болады. Соққылаумен ұсақтау кезінде материалдың жүктелуі импульсты максималды кілт аймақты болуы қажет. Жүктеме ақаулы аймақтың төзімділігі мен беріктілігіне сәйкес мөлшерлі болуы қажет.

Диірменнің жұмыс аймағына бастапқы материал шағын қолемде түсуі қажет, даналап болса тіптен жақсы және ұсақталғаннан соң ұнтақтау аймағынан жылдам шеттетіліп класификаторға жөнелтілуі қажет. Сәйкесінше, кез-келген диірмен түйік циклда жұмыс жасауы қажет.

Дайын өнімге тек шектес бидайдан кіші бөлшектер түсін, ал майдалауға қайтарылатын ірі фракция дайын өнімнің мүмкіндігінше аз бөлшегін құрауы үшін класификатор жоғары тиімділікке ие болуы қажет.

**Түйін сөздер:** ұсақтағыштар, диірмендер, энерго шығындар, ұнтақтың жұқағы, мыжғылау, уату, майдалау, сындырылу, соққы, класификатор, түйік цикл.

УДК 621.926

**Е.В. Опимах<sup>1</sup>, А.Э. Левданский<sup>1</sup>, В.Г. Голубев<sup>2</sup>, Б.Н. Корганбаев<sup>2</sup>, Д. Сарсенбекулы<sup>2</sup>**

<sup>1</sup> Белорусский государственный технологический университет, г. Минск, Беларусь;

<sup>2</sup> Южно-Казахстанский государственный университет им. М. Ауэзова, г. Шымкент, Казахстан

## **ПЕРСПЕКТИВНЫЕ НАПРАВЛЕНИЯ СНИЖЕНИЯ УДЕЛЬНЫХ ЭНЕРГОЗАТРАТ ПРИ ИЗМЕЛЬЧЕНИИ**

**Аннотация.** Процесс измельчения находит широкое применение в различных технологиях и отличается высоким энергопотреблением. Кроме того, происходит безвозвратная потеря высококачественной стали из-за износа рабочих элементов измельчителей.

Высокие энергетические затраты объясняются не только большими объемами перерабатываемых материалов, но и чрезвычайно низкой эффективностью измельчающих машин, особенно мельниц, коэффициент полезного действия (КПД) которых составляет в лучшем случае несколько процентов. Особенно резко снижается КПД и возрастает мощность привода мельниц с увеличением тонины помола материала.

Несмотря на новые способы измельчения: электрогидравлический, ультразвуковой, гравитационный, измельчение световым лучом и т.д., во всех конструкциях промышленных агрегатов измельчение

осуществляется механическими способами, такими как раздавливание, раскалывание, удар, истирание, разламывание или сочетанием этих способов.

Проведен анализ затрат энергии на образование новых поверхностей, на упругие и пластические деформации, на образование различного рода дефектов кристаллической структуры (в основном дислокаций), на трение частиц материала между собой и стенками измельчающей камеры. Отмечено, что незначительная часть подводимой энергии расходуется наразличного рода излучения (акустические волны, экзоэлектронную эмиссию и т.д.), которые всегда сопровождают разрушение.

Из проведенного анализа следует, что наиболее низкая энергоемкость процесса измельчения достигается при измельчении за счет удара и несколько хуже за счет раздавливания. При измельчении ударом нагружение материала должно быть импульсным с максимально крутым фронтом. Нагрузки должны быть дозированными соответствующими прочности и выносливости дефектных зон.

В рабочую зону мельницы исходный материал должен поступать в небольших объемах, а еще лучше поштучно и после измельчения быстро удаляться из зоны помола в классификатор. Следовательно, любая мельница должна работать в замкнутом цикле.

Классификатор должен обладать высокой эффективностью, чтобы в готовый продукт попадали частицы только меньше граничного зерна, а возвращаемая на домол крупная фракция содержала как можно меньше частиц готового продукта.

**Ключевые слова:** измельчители, мельницы, энергозатраты, помола, раздавливание, раскалывание, истирание, разламывание, удар, классификатор, замкнутый цикл

**Information about authors:**

Apimakh Yauheni Vladimirovich - Candidate of Technical Sciences teacher of the Department "Processes and Apparatuses of Chemical Production", Belorussian State Technological University, e-mail: alex\_levdansky@mail.ru;

Leudanski Aliaksandr Eduardovich - Doctor of Technical Sciences, Associate Professor of the Department "Processes and Apparatuses of Chemical Production", Belorussian State Technological University, e-mail: alex\_levdansky@mail.ru;

Golubev Vladimir Grigorievich - Doctor of Technical Sciences, Professor of the Department of Oil & Gas Business, M.Auezov South Kazakhstan State University, e-mail: nii\_mm@mail.ru;

Korganbayev Baurzhan Nogaybayevich - Doctor of Technical Sciences, Professor of the Department of Technological Machines and Equipment, M.Auezov South Kazakhstan State University, e-mail: nii\_mm@mail.ru;

Sarsenbekuly Didar - PhD, teacher of the Department of Technological Machines and Equipment, M.Auezov South Kazakhstan State University, e-mail: nii\_mm@mail.ru.

**МАЗМҰНЫ**

<i>Кантуреева Г.О., Defrancesco E., Алибеков Р.С., Уразбаева К.А., Ефимова И.Е.</i> Қазақстанның дәстүрлі азық-тұлік өнімдерді сәйкестендіру жана тенденциялары .....	6
<i>Туктін Б.Т., Текізбаева А.С., Нұргалиев Н.Н., Шаповалова Л.Б., Яскевич В.И.</i> Модифицирленген Ni(Co)-Mo- Al <sub>2</sub> O <sub>3</sub> катализаторларында тұра айдалған бензин фракциясын гидроизомерлеу және гидроөндіде .....	13
<i>Ахметалимова А.М., Ивасенко С.А., Марченко А.Б., Ишмуратова М.Ю., Полезчак Э., Людвичук А., Лосева И.В.</i> Караганды өніріндегі THYMUS EREMITA KLOK. және THYMUS RASITATUS KLOK. өсімдіктерінің химиялық күрамын зерттеу.....	20
<i>Фазылов С.Д., Нұркенов О.А., Журинов М.Ж., Әрінова А.Е., Туктаров А.Р., Исаева А.Ж., Шаихова Б.К.</i> C <sub>60</sub> фуллеренге гидразондардың палладий комплекстерімен катализденетін циклокосылуы .....	26
<i>Опимах Е.В., Левданский А.Э., Голубев В.Г., Корганбаев Б.Н., Сарсенбекұлы Д.</i> Ұсақтау барысындағы меншікті энергия шығындарын төмөндөтудің келешекті бағыттары .....	32
<i>Қаспәмет М.Ж., Тәжібайева С.М., Уракаев Ф.Х., Уралбеков Б.М., Бұркітбаев М.М., Бачилова Н.В.</i> Нанокүртті алу және турақтандыру .....	41
<i>Байсанов С.О., Толоконникова В.В., Нарықбаева Г.И., Корсукова И.Я., Жучков В.И.</i> Күй диаграммасына талдау жасау негізінде марганецті және хромды ферроқорытпаларды балқытуға термодинамикалық бағалау.....	47
<i>Құлекеев Ж.Ә., Нұртаева Г.Қ., Мұстафин Е.С., Айнабаев А.А., Мұстафин Т.Е., Борсынбаев А.С., Жарикесов F.A.</i> Тенізге төгілген мұнайды жоюда хердерлерді пайдаланудың мүмкіндіктері .....	58
<i>Туктін Б.Т., Нұргалиев Н.Н., Тенизбаева А.С., Шаповалова Л.Б., Комашко Л.В.</i> Бензиннің әртүрлі фракцияларын модифицирленген алюмокобальтмолибден катализаторларында гидрожаксарту .....	67
<i>Қалдыbekова А.Ж., Амангазиева А.Т., Халменова З.Б., Үмбетова А.К.</i> Haplophyllum A. Juss шебінен биологиялық белсенді заттардың кешенді бөліну технологиясын дамыту .....	74
<i>Опимах Е.В., Левданский А.Э., Волненко А.А., Жұмадуллаев Д.К.</i> Флотациялық процесстерді жүргізу әдістері .....	82
<i>Чиркун Д. И., Левданский А. Э., Волненко А.А., Сарсенбекұлы Д.</i> Соққылы-ортадан тепкіш дайрмендердегі бөлшектердің динамикасын зерттеу .....	92
<i>Баймұшашева Г.К., Қалауова А.С., Құспанова Б.К., Насиров Р.Н.</i> Ушфенилфосфиннің анион-радикалы.....	102
<i>Баешова А.К., Молайған С., Баевшов А.Б.</i> Сутектік энергетиканың қазіргі замандағы жағдайы және сутекті алу әдістері .....	107
<i>Закарина Н.А., Дәлелханұлы О., Жұмадуллаев Д.А., Ақурлекова А.К., Джумабаева Л.С.</i> Al, AlZr және Ti-мен пилларирленген Na- және Ca-формалы монтмориллонитке енгізілген Pt- және Pd-катализаторларындағы тікелей айдалған бензиннің жеңіл фракцияның изомеризациясы.....	117
<i>Нәсиров Р.Н.</i> ЭПР спектроскопия көмегімен каспий маңындағы мұнайлардағы ванадийді анықтау.....	125
<i>Байжуманова Т.С., Тунгатарова С.А., Xanthopoulou G., Жексенбаева З.Т., Кауменова Г.Н., Еркибаева М.К., Жұмабек М., Касымхан К.</i> Метанның олефиндерге дейін катализикалық конверсиясы.....	132
<i>Калимукашева А.Д., Калиманова Д.Ж., Иманкулова З.А.</i> Формативті бағалау-химия сабактарында оқыту процесінің ажырамас бөлігі.....	139
<i>Масенова А.Т., Калықбердиев М.К., Сасс А.С., Кензин Н.Р., Канатбаев Е.Т., Цыганков В.П.</i> Бензин фракцияларындағы хош иісті көмірсүтектерді жоғары қысымда отырғызылғын катализаторларды қолдану арқылы сутектендіру.....	146

## СОДЕРЖАНИЕ

<i>Кантуреева Г.О., Defrancesco E., Алибеков Р.С., Уразбаева К.А., Ефимова И.Е.</i> Новые тенденции в идентификации традиционной пищевой продукции Казахстана .....	6
<i>Туктун Б.Т., Тенизбаева А.С., Нургалиев Н.Н., Шаповалова Л.Б., Яскевич В.И.</i> Исследование гидроочистки и гидроизомеризации прямогонной бензиновой фракции на модифицированных Ni(Co)-Мо- Al <sub>2</sub> O <sub>3</sub> - катализаторах .....	13
<i>Ахметалимова А.М., Ивасенко С.А., Марченко А.Б., Ишмуратова М.Ю., Полезчак Э., Людвичук А., Лосева И.В.</i> Исследование химического состава <i>THYMUS EREMITA KLOK</i> и <i>THYMUS RASITATUS KLOK</i> . Карагандинского региона .....	20
<i>Фазылов С.Д., Нуркенов О.А., Журинов М.Ж., Аринова А.Е., Туктаров А.Р., Исаева А.Ж., Шаихова Б.К.</i> Катализируемое комплексами палладияциклогипсоединение гидразонов к фуллерену C <sub>60</sub> .....	26
<i>Опимах Е.В., Левданский А.Э., Голубев В.Г., Корганбаев Б.Н., Сарсенбекулы Д.</i> Перспективные направления снижения удельных энергозатрат при измельчении .....	32
<i>Кансамет М.Ж., Тажибаева С.М., Уракаев Ф.Х., Уралбеков Б.М., Буркитбаев М.М., Бачилова Н.В.</i> Получение и стабилизация наносеры .....	41
<i>Байсанов С.О., Толоконникова В.В., Нарикбаева Г.И., Корсукова И.Я., Жучков В.И.</i> Термодинамическая оценка выплавки марганцевых и хромистых ферросплавов на основе анализа их диаграмм состояния.....	47
<i>Кулекеев Ж.А., Нуртаева Г.К., Мустафин Е.С., Айнабаев А.А., Мустафин Т.Е., Борсынбаев А.С., Жарикесов Г.А.</i> Возможности использования хердеров при ликвидации разливов нефти на море .....	58
<i>Туктун Б.Т., Нургалиев Н.Н., Тенизбаева А.С., Шаповалова Л.Б., Комашко Л.В.</i> Гидрооблагораживание различных бензиновых фракций намодифицированных алюмокобальтмолибденовых катализаторах .....	67
<i>Калдыбекова А.Ж., Амангазиева А.Т., Халменова З.Б., Умбетова А.К.</i> Разработка технологии комплексного выделения биологических активных веществ из растений рода <i>Haplophyllum</i> A. Juss .....	74
<i>Опимах Е.В., Левданский А.Э., Волненко А.А., Жумадуллаев Д.К.</i> Методы проведения флотационных процессов .....	82
<i>Чиркун Д. И., Левданский А. Э., Волненко А.А., Сарсенбекулы Д.</i> Исследование динамики частиц в ударно-центробежных мельницах .....	92
<i>Баймукашева Г.К., Калауова А.С., Куспанова Б.К., Насиров Р.Н.</i> Анион-радикал трифенил-фосфина.....	102
<i>Баешова А.К., Молайган С., Баев А.Б.</i> Современное состояние водородной энергетики и способы получения водорода.....	107
<i>Закарина Н.А., Дәлелханұлы О., Жумадуллаев Д.А., Ақурекова А.К., Джумабаева Л.С.</i> Изомеризация легкой фракции прямогонного бензина на Pt- и Pd-катализаторах, нанесенных на пилларированный Al, AlZr и Ti монтмориллонит в Na- и Ca-формах.....	117
<i>Насиров Р.Н.</i> Определение ванадия в нефтях прикаспийского региона методом ЭПР-спектроскопии.....	125
<i>Байжуманова Т.С., Тунгатарова С.А., Xanthopoulou G., Жексенбаева З.Т., Кауменова Г.Н., Еркибаева М.К., Жумабек М., Касымхан К.</i> Каталитическая конверсия метана в олефины.....	132
<i>Калимукашева А.Д., Калимanova Д.Ж., Иманкулова З.А.</i> Формативное оценивание - неотъемлемая часть процесса обучения на уроках химии.....	139
<i>Масенова А.Т., Калықбердиев М.К., Сасс А.С., Кензин Н.Р., Канатбаев Е.Т., Цыганков В.П.</i> Гидрирование ароматических углеводородов в бензиновых фракциях на нанесенных катализаторах под давлением.....	146

**CONTENTS**

<i>Kantureeva G.O., Defrancesco E., Alibekov R.S., Urazbayeva K.A., Efimova I.E.</i> New trends in the identification of the traditional food products of Kazakhstan .....	6
<i>Tuktin B.T., Tenizbaeva A.S., Nurgaliyev N.N., Shapovalova L.B., Yaskevich V.I.</i> Study of hydro purification and hydroisomerization straight-run gasoline fraction over modified Ni(Co)-Mo- $\text{Al}_2\text{O}_3$ - catalysts .....	13
<i>Akhmetalimova A.M., Ivasenko S.A., Marchenko A.B., Ishmuratova M.Yu., Poleszak E., Ludwiczuk A., Loseva I.V.</i> The study of the chemical composition of <i>THYMUS EREMITA</i> KLOK. and <i>THYMUS RASITATUS</i> KLOK. from the Karaganda region .....	20
<i>Fazylov S.D., Nurkenov O.A., Zhurinov M.Zh., Arinova A.E., Tuktarov A.R., Issayeva A.Zh., Shaihova B.K.</i> Catalyzed by palladium complexes the cycloaddition of hydrazones to fullerenec <sub>60</sub> (in English).....	26
<i>Apimakh Ye.V., Leudanski A.E., Golubev V.G., Korganbayev B.N., Sarsenbekuly D.</i> Promising directions of reducing specific energy costs in grinding (in English).....	32
<i>Kapsamet M.Zh., Tazhibayeva S.M., Urakaev F.Kh., Uralbekov B.M., Burkutbayev M.M., Bachilova N.V.</i> Obtaining and stabilization of nanosulfur .....	41
<i>Baisanov S.O., Tolokonnikova V.V., Narikbayeva G.I., Korsukova I.Ya., Zhuchkov V.I.</i> Thermodynamic assessment of smelting of manganese and chromium ferroalloys based on the analysis of their state diagrams .....	47
<i>Kulekeyev Zh.A., Nurtayeva G.K., Mustafin E.S., Ainabayev A.A., Mustafin T.E., Borsynbayev A.S., Zharikessov G.A.</i> Using herders for oil spill response in the sea .....	58
<i>Tuktin B.T., Nurgaliyev N.N., Tenizbaeva A.S., Shapovalova L.B., Komashko L.V.</i> Hydrotreating of various petrol fractions over modified alumocobaltmolybdenic catalysts .....	67
<i>Kaldybekova A.Zh., Amangazyeva A.T., Halmenova Z.B., Umbetova A.K.</i> Development of technology for the complex isolation of biological active substances from plants of the genus <i>Haplophyllum</i> A. Juss .....	74
<i>Apimakh Ye.V., Leudanski A.E., Volnenko A.A., Zhumadullaev D.K.</i> Methods of carrying out flotation processes .....	82
<i>Chyrkun D.I., Levdanskiy A.E., Volnenko A.A., Sarsenbekuly D.</i> Study of the particle dynamics in impact-centrifugal mills (in English).....	92
<i>Baymukasheva G.K., Kalauova A.S., Kuspanova B., Nasirov R.N.</i> Triphenylphosphine anion radical.....	102
<i>Bayeshova A.K., Molaigan S., Bayeshov A.B.</i> Hydrogen energetics current state and hydrogen production methods.....	107
<i>Zakarina N.A., Dolelkhanuly O., Jumadullaev D.A., Akurpekova A.K., Djumabaeva L.S.</i> Isomerization of light fraction of straight-run gasoline on Pt-and Pd-catalysts supported on pillared by Al, AlZr and Ti montmorillonite in Na-and Ca-forms..	117
<i>Nasirov R.N.</i> Determination of vanadium in the precaspian region's oil by the EPR-spectroscopy method.....	125
<i>Baizhumanova T.S., Tungatarova S.A., Xanthopoulou G., Zheksenbaeva Z.T., Kaumenova G.N., Erkibaeva M.K., Zhumabek M., Kassymkan K.</i> Catalytic conversion of methane into olefins.....	132
<i>Kalimukasheva A.D., Kalimanova D.Z., Imankulova Z.A.</i> Formative evaluation is an uninterrupted part of the training process on lessons of chemistry.....	139
<i>Massenova A.T., Kalykberdiyev M.K., Sass A.S., Kenzin N.R., Kanatbayev E.T., Tsygankov V.P.</i> Hydrogenation of aromatic hydrocarbons in gasoline fractions over supported catalysts under pressure.....	146

---

## **Publication Ethics and Publication Malpractice in the journals of the National Academy of Sciences of the Republic of Kazakhstan**

For information on Ethics in publishing and Ethical guidelines for journal publication see <http://www.elsevier.com/publishingethics> and <http://www.elsevier.com/journal-authors/ethics>.

Submission of an article to the National Academy of Sciences of the Republic of Kazakhstan implies that the described work has not been published previously (except in the form of an abstract or as part of a published lecture or academic thesis or as an electronic preprint, see <http://www.elsevier.com/postingpolicy>), that it is not under consideration for publication elsewhere, that its publication is approved by all authors and tacitly or explicitly by the responsible authorities where the work was carried out, and that, if accepted, it will not be published elsewhere in the same form, in English or in any other language, including electronically without the written consent of the copyright-holder. In particular, translations into English of papers already published in another language are not accepted.

No other forms of scientific misconduct are allowed, such as plagiarism, falsification, fraudulent data, incorrect interpretation of other works, incorrect citations, etc. The National Academy of Sciences of the Republic of Kazakhstan follows the Code of Conduct of the Committee on Publication Ethics (COPE), and follows the COPE Flowcharts for Resolving Cases of Suspected Misconduct ([http://publicationethics.org/files/u2/New\\_Code.pdf](http://publicationethics.org/files/u2/New_Code.pdf)). To verify originality, your article may be checked by the Cross Check originality detection service <http://www.elsevier.com/editors/plagdetect>.

The authors are obliged to participate in peer review process and be ready to provide corrections, clarifications, retractions and apologies when needed. All authors of a paper should have significantly contributed to the research.

The reviewers should provide objective judgments and should point out relevant published works which are not yet cited. Reviewed articles should be treated confidentially. The reviewers will be chosen in such a way that there is no conflict of interests with respect to the research, the authors and/or the research funders.

The editors have complete responsibility and authority to reject or accept a paper, and they will only accept a paper when reasonably certain. They will preserve anonymity of reviewers and promote publication of corrections, clarifications, retractions and apologies when needed. The acceptance of a paper automatically implies the copyright transfer to the National Academy of Sciences of the Republic of Kazakhstan.

The Editorial Board of the National Academy of Sciences of the Republic of Kazakhstan will monitor and safeguard publishing ethics.

Правила оформления статьи для публикации  
в журнале смотреть на сайте:

[www.nauka-nanrk.kz](http://www.nauka-nanrk.kz)

<http://www.chemistry-technology.kz/index.php/ru/>

**ISSN 2518-1491 (Online), ISSN 2224-5286 (Print)**

Редакторы: *M. С. Ахметова, Т. А. Апендиев, Аленов Д.С.*  
Верстка на компьютере *А.М. Кульгинбаевой*

Подписано в печать 11.10.2018.  
Формат 60x881/8. Бумага офсетная. Печать – ризограф.  
9,8 п.л. Тираж 300. Заказ 5.

---

*Национальная академия наук РК*  
050010, Алматы, ул. Шевченко, 28, т. 272-13-18, 272-13-19